



Product Description

Acti-Gel[®] 208 is a low-dose rheology modifier and anti-settling agent that stabilizes mixtures, provides superior aggregate suspension, and dramatically improves the performance and paste quality of concretes. When fully dispersed, Acti-Gel[®] 208 particles form a unique lattice 'microstructure' that supports slightly higher yield stress and thixotropy, resulting in a greater ability to suspend both cement particles and aggregate with reduced segregation and bleed. Under conditions of shear, flow conditions are enhanced resulting in improved pumpability and workability. Some designs may result in a reduction in measured slump. Please see optimizing recommendations below.

Acti-Gel[®] 208 is made from a highly purified Mg-aluminosilicate using a patented process. It is non-swelling and shear stable in both low and high salt environments and between pH 2-13.

Acti-Gel[®] 208 is neutral setting and will not affect air contents.

Acti-Gel[®] 208 complies with ASTM C 494, Type S.

Packaging

Acti-Gel[®] 208 is available in liquid or powder form.

Applications:

- Mortar grouts
- Neat cement grouts
- Flowable fill

Benefits:

- Increases pumpability
- Eliminates segregation
- Optimizes designs
- Mix stability



Performance

Acti-Gel[®] 208 is a thixotropic material that suspends particles, reduces segregation, and dramatically stabilizes concretes. During mixing or emplacement flow is greatly enhanced due to its shear-thinning behavior. On removal of shear, the rate of thixotropic rebuilding of the lattice structure is exceptionally fast, which provides i) superior cohesion, ii) rapid development of green strength and shape stability, iii) excellent anti-washout properties, and iv) reduction in hydrostatic pressure.

When used in an optimized mix design, Acti-Gel[®] 208 has been shown to increase green strength, decrease rapid chloride permeability, and reduce efflorescence – all with outstanding stability and compaction. **Please contact your local representative for recommendations.**



Acti-Gel® 208 addition will help provide consistent and precise performance in critical grouting operations. It can be used in underwater grouting applications where highly flowable, non-shrink grout with excellent cohesion is needed for placement or repairs.

Guidelines for Use

Acti-Gel® 208 can be added in the mixing sequence at various stages depending on the application, using a recommended dry dosage of ~2.5 lbs. per yd^3 or ~1 gallon per yd^3 . **Please contact your local representative for recommendations** and to schedule a free on-site plant trial.

Optimizing Acti-Gel® 208

The performance of Acti-Gel® 208 is dependent on mix proportions, local materials, cement chemistry, fineness of materials, and w/c ratio. Potential mix designs for specific applications should be evaluated using actual project materials to ensure that the chosen mix design meets project specifications. **Please contact your local representative for recommendations.**

Product Data Sheet, Rev. Jan 2017

Recommendations and advice concerning dosages, application, performance, and use is provided in good faith, based on our testing, experience, and knowledge of the product under normal conditions. All claims based on performance are believed to be accurate. No guarantee, either expressed or implied, is made with reference to the infringement of any patent. These values represent typical data from samples taken from production batches. They are not considered to be specifications. Results may vary depending upon equipment and procedures. The user of these materials is responsible for determining its suitability for their application with different materials and actual site conditions.