

## 2200 TEXWALL ULTRA SUPER HARD TEXTURE SYSTEM



### DESCRIPTION:

- Designed as a single product, two-coat system that provides a ultra-tough, durable, breathable decorative commercial textured wall finish on interior walls.
- Acrylic breakthrough product that is pigment rich and contains no cement or plaster compounds.
- Remains slightly flexible when cured thereby making it extremely resistant to cracking and chipping under the most demanding commercial/hospitality environment.
- A 100% acrylic resin Super Hard Texture Base.
- Mildew resistant - this texture coating contains agents which inhibit the growth of mildew on the surface of this texture film.
- Formulated using the latest technology. This product is designed to produce a tough, durable, breathable, decorative texture coat on interior drywall and masonry.
- Durability, adhesion and ease of maintenance.
- Excellent vapor transmission and resists the condensation and it's damage which is common in the walls of motel, hotel, apartment, office and other buildings.

### ORDERING:

- Available in 5 gallon buckets only.
- Coverage:
  - **As a color base**, 200 sq. ft./gallon
  - **As the texture coat**, 125 sq. ft./gallon (depending on the texture pattern desired, method of application and equipment used).

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
2200 TEXWALL ULTRA TINT BASE	220005	5G	760428220052	12" x 12" x 15"	1	36 Cases

### STORAGE & HANDLING:

- **Warning!** If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure. Wear an NIOSH-approved respirator to control lead exposure.
- To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying.
- If you experience eye watering, headaches or dizziness, increase fresh air.
- A dust mask does not provide protection against vapors.
- Use only with adequate ventilation.
- Wash thoroughly after handling.
- Clean up carefully with a HEPA vacuum and a wet mop.
- **KEEP AWAY FROM CHILDREN.**
- **KEEP FROM FREEZING**
- **FIRST AID:** In case of skin contact, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. **For eye contact**, flush immediately with large amounts of water, for at least 15 minutes. **If swallowed**, get medical attention immediately. **If inhalation causes physical discomfort**, move to fresh air. **If discomfort persists** or any breathing difficulty occurs, get medical help.

### PRECAUTIONS:

- Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**
- **Warning! Irritant!** Harmful if swallowed, when tinted, contains ethylene glycol which can cause severe kidney damage when ingested and has been shown to cause birth defects in laboratory animals.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- May cause eye, nose and throat irritation.
- Do not take internally.
- Do not breathe vapors or spray mist.
- Avoid contact with skin and eyes. Wear eye protection and protective clothing.
- **For emergency information call (800) 545-2643.**
- For additional safety information, refer to the Safety Data Sheet for this product.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- Close container after each use.



**WARNING:** This product can expose you to chemicals including Titanium Dioxide, which is known to the State of California to cause cancer. For more information go to [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

# 2200 TEXWALL ULTRA SUPER HARD TEXTURE SYSTEM

PROPERTIES	
Weight per Gallon	13.30 lbs.
Color(s)	Tint Base Up to 8 oz. universal colorant per gallon
VOC Content	Under 250 G/L (cal.)
Viscosity	135+ KU @ 77° F
Solid Content by Weight	67.8%
Solid Content by Volume	48.8%
Resin	100% Acrylic modified for superior durability & scrubability
Flash Point	None
Permeance	(ASTM D-1653) 30+
Mildew Growth	(MIL SPEC 810E) 0%
Fire & Smoke	(ASTM E84) non-combustible Class A
Scrubability	(ASTM D-2486) 4,000+ cycles no erosion
Pencil Hardness	(ASTM D-3363) 4H
Total System DFT	14-19 mils
Dry Time @ 75° F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 2 Hours To Recoat: 4 Hours Full Cure: 7 Days

## APPLICATION KNOCKDOWN

- Spray applied multiple coat interior wall system to achieve a knockdown texture finish.
- Apply at package consistency by hopper gun or through a texture pump and gun.
- Obtain “knock down” effect by smoothing the peaks with a stainless steel trowel.
- Drying time to achieve desired “knock down effect” will vary due to temperature, humidity and other conditions and is best determined by test applications.
- Can be troweled on with a stainless steel trowel.
- Always work to a wet edge.
- Varying orifice size, air pressure and knock down technique will have an effect on finished appearance.
- Experimentation and test application is recommended.
- Once a procedure has been determined to achieve desired results all changes including applicator should be avoided until a different wall or natural breaking point has been reached.

## TINT SYSTEM

- Use 1/2 the 5 gallon formula to achieve medium to pastel shades.

## CLEANUP:

- Clean all equipment and overspray immediately with warm soapy water.
- Dried material is very difficult to remove.

## DIRECTIONS FOR USE AND SURFACE PREPARATION:

### APPLICATION COLOR BASE COAT RENOVATION or NEW WORK:

- Surface must be clean, dry, sound and paint ready.
- Mix the material thoroughly using a slow speed drill with a joint compound blade. Apply with airless sprayer using a .023 - .025 tip in a mastic gun and a 3/8” material hose.
- Achieve 4 mil dry film thickness by applying 8 mils wet at an application rate of 200 sq. ft./gallon.
- Thin with water (1/2-gallon water to 5 gallons TexWall Ultra) to ease airless sprayer application.
- Make sure airless equipment selected has sufficient capacity to support tip selected.
- A test application is recommended to determine actual coverage under specific job conditions.