



### DESCRIPTION:

- Fast drying, water clean up, environmentally friendly, Specially formulated interior dry wall primer that ensures the finish coat of paint will look its best.
- Covers and primes the differences between the texture variations of gypsum board paper and joint compound finishes to a level 5 finish from a level 4 finish.
- Helps to equalize the porosity and surface texture differences found in new construction dry wall installations, typically called "joint banding".
- Forms a tight dry film, formulated with "plating technology" which delivers excellent dry film hold out characteristics for satin and semi-gloss top coats.
- Formulated for use on interior new construction drywall, or concrete surfaces.
- Produces an excellent prime finish for walls in homes, hotels, motels, offices and apartments that require a uniform beautifully finished wall appearance.

### ORDERING:

- Available in 5 gallon buckets only.
- Coverage is between 300 to 500 square feet per gallon, per coat, depending on the type of surface and porosity.

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
1815 TEXWALL RESURFACER 5G	181505	5G	760428181551	12" x 12" x 15"	1	36 Cases

### STORAGE & HANDLING:

- **CONTAINS SOLVENTS, WHICH CAN CAUSE PERMANENT BRAIN AND NERVOUS SYSTEM DAMAGE.**
- **Warning!** If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure. Wear an NIOSH-approved respirator to control lead exposure.
- To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying.
- If you experience eye watering, headaches or dizziness, increase fresh air.
- A dust mask does not provide protection against vapors.
- Use only with adequate ventilation.
- Wash thoroughly after handling.
- Clean up carefully with a HEPA vacuum and a wet mop.
- **KEEP AWAY FROM CHILDREN.**
- **KEEP FROM FREEZING**
- **FIRST AID:** In case of skin contact, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. For eye contact, flush immediately with large amounts of water, for at least 15 minutes. If swallowed, get medical attention immediately. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help.

### PRECAUTIONS:

- Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**
- **Warning! Irritant!** Harmful if swallowed.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- May cause eye, nose and throat irritation.
- Do not take internally.
- Do not breathe vapors or spray mist.
- Avoid contact with skin and eyes. Wear eye protection and protective clothing.
- **For emergency information call (800) 545-2643.**
- For additional safety information, refer to the Safety Data Sheet for this product.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- Close container after each use.



**WARNING:** This product can expose you to chemicals including Titanium Dioxide, which is known to the State of California to cause cancer. For more information go to [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

# 1815 TEXWALL RESURFACER / PRIMER

PROPERTIES	
Weight per Gallon	11.31 lbs.
Color(s)	White, may be tinted up to 4 oz. Universal Colorant
Gloss	Matte
VOC Content	93.2 Grams per Liter (cal.)
Viscosity	108 KU @ 75° F
Solid Content by Weight	47.5%
Solid Content by Volume	29.08%
Pigment by weight	41.0%
Vehicle by weight	6.50%
Resin	Vinyl Acrylic
Dry Time @ 70°F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 1 Hour To Recoat: 2 to 3 Hours Full Cure: 24 Hours

## COVERAGE:

- Average coverage is 300 to 500 square feet per gallon. A test application is recommended to determine actual coverage under specific job conditions.
- Coverage will vary greatly depending upon method of application, surface condition and technique of the applicator.

## APPLICATION:

- Maintain minimum air, product and surface temperature of 50° F or above during application and until surface is dry, approximately 30 minutes to 1 hour under 77° F / 50% RH.
- Apply by brush, roller or suitable airless spray unit at package consistency.
- The airless sprayer should be capable of delivering more than 3/4 gallon a minute.
- Remove all in-line filters.
- Use a 3/8" material hose and a 19 to 21 tip at 1700 to 2200 psi. Always work to a wet edge overlapping 1/4 to 1/2 the fan width.
- Varying orifice size, pressure and technique will have an effect on coverage rates.
- Roller application is best achieved using a 1/8" to 1/4" high quality nap roller designed for smooth surfaces.

## THINNING

Not recommended

## DIRECTIONS FOR USE AND SURFACE PREPARATION:

- If used under wallpaper, a wallpaper primer or size should also be used.
- Not recommended for new plaster.

## SURFACE PREPARATION:

- Substrate must be clean, dry, sound and PAINT READY.
- Wall surfaces should be dry, free of dust, grime or other contaminants that could interfere with the bonding characteristics of Anvil Texwall Resurfacer/Primer.
- Product, air and surface temperatures must be maintained at a minimum of 50°F.
- New masonry must be allowed to cure for at least 30 days.
- Repair any significant voids, cracks and fastener holes.
- Check all corner beads or exposed nail and screw heads that are likely to produce rust in the future and prime with a stain blocking metal primer.
- On walls stained from mildew, water, grease or other causes, a stain blocking primer should be applied to reduce flashing.

## CLEANUP:

- Clean all equipment with warm soapy water.