












- Watertight asphalt to asphalt lap system
- 30 Year limited warranty
- TITANIUM PSU30 is an approved Polyfoam underlayment for use with Polyset® foam systems
- The only modified rubberized asphalt Peel & Stick with a tough and rugged walking surface
- Class A Fire ASTM E108
- Meets and exceeds ASTM D226
- All temperature performance -40°F to 240°F (-40°C to 115°C) Installation temperature 40°F (5°C) and above
- Patented Sure-Foot® slip resistant technology
- Synthetic construction inert to mold growth
- Cool light gray surface, doesn't expand or contract
- Up to 6 Months UV exposure

#### **SPECIFICATIONS**

| LENGTH PER ROLL:  | 72′ / 22 m        |
|-------------------|-------------------|
| WIDTH PER ROLL:   | 36" / 91.4 cm     |
| WEIGHT PER ROLL:  | 48 lbs / 22 kg    |
| NET ROLL SIZE:    | 2 sq / 20 m²      |
| ROLLS PER PALLET: | 25                |
| PALLET WEIGHT:    | 1300 lbs / 590 kg |

# ICE DAMMING & LEAK PROTECTION HIGH & LOW TEMPERATURE PEEL & STICK AIR, WATER & VAPOR BARRIER

## FOR USE UNDER ALL: METAL, TILE, SLATE, SHAKE & SHINGLE ROOFING





Miami-Dade County Product Control Approved NOA No.: 11-0815.05 CAN/CSA A220.1 FLORIDA BUILDING CODE CLASS A ASTM-E108 FIBREGLASS SHINGLES







### **TECHNICAL DATA**

| ILCHINICAL DAIA      |                     | <b>25</b> 11 1000  |
|----------------------|---------------------|--|
| TEST & PROPERTIES    | STANDARD            | TITANIUM® PSU30 TYPICAL VALUE                                  |
| Color                |                     | Gray   |
| Surface              |                     | Synthetic Polymer - Patented Sure-Foot® slip resistant nodular |
| Release Liner        |                     | Silicone Treated, Crinkled Poly Split Release                  |
| Weight per square    |                     | 24 lbs / (10.8 kg)   |
| Nail Sealability     | ASTM D1970 Modified | Pass   |
| Permeability         | ASTM E96            | 0.0336   |
| Nominal Thickness    | ASTM D5147          | 45 Mil (1.1 mm)  |
| Tensile              | ASTM D1970          | MD 100 lbs/in/ (17.5 kN/m)   CD 80 lbs/in (14 kN/m)            |
| Thermal Stability    | ASTM D1970          | 240° F (115° C) Pass   |
| Low Temp Flexibility | ICC AC 48           | Pass   |
| Tear Resistance      | ASTM D1970          | MD 140/ CD 100 lbf (622/445 N)                                 |
| Adhesion to Plywood  | ASTM D903           | 4 lb/in (700 N/m)  |
| Temperature Range    |                     | -40°F to 240°F (-40°C to 115°C)                                |



## InterWrap® Roofing Products Division

lest data is based on average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications. All values ± 10 %. PSU30\_SS\_6June2014