



■ DX-250B/4F Drain Board

DX-250B/4F Drain Board consists of a light duty impermeable polymeric sheet cusped under heat and pressure to form a high flow dimpled drainage core. The core is then bonded to a layer of non-woven filter fabric. The filter fabric retains soil or sand particles as well as freshly placed concrete or grout, allowing filtered water to pass into the drainage core. Limited to 20 feet of backfill.

DX-250B/4F has identical properties to DX-250B/4 with the addition of a protective sheet bonded to the backside of the cusped core providing protection for soft membrane waterproofing systems.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> Core			
Compressive Strength	ASTM D 1621	527 kNm ²	11,000 psf
Thickness	ASTM D 1777	10.16 mm	.40 in
Flow (Hydraulic gradient=1)	ASTM D 4716	223 l/min/m	18 g/min/ft
<input type="checkbox"/> Fabric			
Flow	ASTM D 4491	5704 l/min/m ²	140 gal/min/ft ²
CBR Puncture	ASTM D 6241	1.113 kN	250 lbs
AOS	ASTM D 4751	.212 mm	70 U.S. Sieve
Grab Tensile	ASTM D 4632	0.45 kN	100 lbs
<input type="checkbox"/> Physical			
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	1.22 m x 15.24 m 18.59 m ² 17 kg	4 ft x 50 ft 200 ft ² 38 lbs
		1.98 m x 15.24 m 30.18 m ² 27 kg	6.5 ft x 50 ft 325 ft ² 61 lbs
		2.44 m x 15.24 m 37.19 m ² 34 kg	8 ft x 50 ft 400 ft ² 76 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288-15 and has been replaced with CBR Puncture ASTM D 6241.

- At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-19 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.