



## ■ DX<sup>®</sup>-2200N/44 Geocomposite

DX-2200N/44 geocomposite consists of an HDPE geonet drainage core with a filter fabric bonded to both sides. The geonet drainage core is virtually crush proof, yet flexible enough to conform to irregular surfaces. Due to the crush proof nature, geonet drainage composites can be used in the most extreme cases with heavy loads and/or heavy vehicular traffic.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> <b>Core</b>			
Compressive Strength	ASTM D 1621	1915 kNm <sup>2</sup>	40,000 psf
Thickness	ASTM D 1777	250 mil	0.25"
Flow Rate	ASTM D 4716	106 l/min/m	8.5 gal/min/ft
<input type="checkbox"/> <b>Fabric</b>			
Grab Tensile	ASTM D 4632	0.445 kN	100 lbs
CBR Puncture	ASTM D 6241	1.113 kN	250 lbs
Flow Rate	ASTM D 4491	5704 l/min/m <sup>2</sup>	140 gal/min/ft <sup>2</sup>
Apparent Opening Size (AOS)	ASTM D 4751	0.212 mm	70 U.S Std. Sieve
<input type="checkbox"/> <b>Composite (Physical/Dimensional)</b>			
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	1.22 m x 22.86 m 27.87 m <sup>2</sup>	4 ft x 75 ft 300 ft <sup>2</sup>

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-19 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.