



REINFORCING SUCCESS

PRODUCT DATA SHEET WINFAB UX900



WINFAB UX900 is a geogrid manufactured with high tenacity multifilament polyester yarns that are woven under tension and finished with a PVC coating to form a dimensionally stable network, which allows the yarns to maintain their relative position.

WINFAB UX900 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Aperture Dimensions	Measured	0.61 in x 1.0 in	1.56 mm x 2.54 mm
Ultimate Tensile Strength (MD)	ASTM D6637	9,000 lbs/ft	131.31 kN/m
Creep Limited Strength (MD)	ASTM D5262	5,696 lbs/ft	83.10 kN/M
T _{al} = Long Term Design Strength (MD)	NCMA97	4,932 lbs/ft	71.96 kN/m

RF Creep - 1.58

RF Durability - 1.10

RF Installation Damage (Soil Type 3) - 1.05

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	6 ft x 150 ft 12 ft x 150 ft	1.83 m x 45.72 m 3.66 m x 45.72 m
Roll Area	Measured	100 yd ² 200 yd ²	83.61 m ² 167.23 m ²

Disclaimer: WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.