





## TECHNICAL INFORMATION, CONTINUED:

Cure Time, Regular Cure (77 degrees, 25% R.H.)	
Dry to Touch	3 hours
Light Traffic	12 hours
Vehicle Traffic	5 days
Full Chemical Resistance	7 days

Cure Time, Fast Cure (77 degrees, 25% R.H.)	
Dry to Touch	2 hours
Light Traffic	6 hours
Vehicle Traffic	24 hours
Full Chemical Resistance	72 hours

Cure Time, Fast Cure (30 degrees, 25% R.H.)	
Dry to Touch	3 hours
Light Traffic	9 hours
Vehicle Traffic	48 hours
Full Chemical Resistance	72 hours

Performance Properties	
Gloss (60 degrees)	95
Hardness (Pendulum)	172
Tabor Abrasion (1000 gm. Load cycles, CS 17 wheel)	36 mg. loss

## CHEMICAL AND STAIN RESISTANCE (ASTM D-1308 24 HOURS IMMERSION):

Urine	No effect
Blood	No effect
Whiskey	No effect
Black Ink	No effect
Brake Fluid	No effect
Gasoline	No effect
Skydrol B-4	No effect
Hydraulic Fluid #83282	No effect
Mineral Spirits	No effect
Xylene	No effect
MEK	Film softened
50% Sodium Hydroxide	No effect
25% Hydrochloric Acid	No effect
25% Sulfuric Acid	No effect
25% Acetic Acid	No effect
25% Nitric Acid	Film blistered

Super-Krete® Products is a Division of Arizona Polymer Flooring, Inc.

© 2017 Arizona Polymer Flooring, Inc  
 4565 W Watkins St. / Phoenix, AZ 85043 / 800.562.4921  
 623.435.2277 Tel. / 623.435.8585 Fax

[www.super-krete.com](http://www.super-krete.com)

SK-P5100 032717



**LIMITATIONS:**

- Do not use on unprimed substrates.
- Do not allow to puddle. Film thickness must not exceed 16 mils.

**WARRANTY:**

Arizona Polymer Flooring guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ARIZONA POLYMER FLOORING MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Arizona Polymer Flooring shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Arizona Polymer Flooring shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.

**Super-Krete® Products is a Division of Arizona Polymer Flooring, Inc.**

© 2017 Arizona Polymer Flooring, Inc  
4565 W Watkins St. / Phoenix, AZ 85043 / 800.562.4921  
623.435.2277 Tel. / 623.435.8585 Fax

[www.super-krete.com](http://www.super-krete.com)

SK-P5100 032717

