



1950 CHATTAHOOCHEE STONE SEALER & GLAZE



RESIN: Silicone Modified Acrylic

COLOR: Clear

SOLID CONTENT:
BY WEIGHT: 21.0%

VISCOSITY: 1,000 cps

WEIGHT PER GALLON: 6.8 lbs

FLASH POINT: 105°F

RECOMMENDED COVERAGE:
100 sq. ft. per gallon, per coat,
depending on the type size of stone
and porosity.

DRYING TIME@70° F & 50% R H

To touch: 15 to 20 minutes
To recoat: 4 to 8 hours
Full Cure: 24 hours

Drying times are influenced by
ambient temperature and relative
humidity.

CLEANUP: Mineral Spirits

TINTING: Not applicable

VOC: 580 grams/liter

1950
AVAILABLE IN
1 AND 5 GALLON



WARNING!
COMBUSTIBLE.
HARMFUL OR FATAL
IF SWALLOWED.

DISPOSAL: Contains Organic Solvents which may cause adverse effects to the environment if disposed of improperly. Place opened, empty containers in normal refuse for disposal. Contact your sanitation department or household hazardous waste coordinator for information concerning re-use, recycling or disposal of solvent-borne paint.

LIMITED WARRANTY AND LIMITATION OF REMEDIES

Anvil Paints & Coatings, Inc., disclaims all expressed warranties except those that appear above. Further, seller disclaims any implied warranty of merchantability of the goods or of the fitness of the goods for any purpose. To the extent allowed by law, any implied warrant of merchantability of fitness applicable to the sealer is limited to the five (5) year duration of the express warranty and is subject to all the terms and conditions of this limited warranty. Purchaser agrees that in no case shall Anvil Paints & Coatings, Inc. be liable for labor, incidental or consequential damages based upon any legal theory including, but not limited to, damages for loss of profits and/or damage to property or failure due to structural defects, acts of God or causes beyond our control, including the negligence of any person, and any other abuse or misuse of this product by purchaser.

5-YEAR WARRANTY

This product is manufactured to rigid quality control specifications. Anvil Paints & Coatings, Inc. warrants to the original purchaser only, that Anvil 1950 Solvent Based Chattahoochee Stone Sealer will be free of manufacturing defects for 5 years from date of purchase when applied in three coats, according to instructions as indicated. If purchaser discovers that Anvil 1950 Solvent Based Chattahoochee Stone Sealer has not performed as stated, promptly send written notification of this fact, along with proof of purchase, to Anvil Paints & Coatings, Inc., 1255 Starkey Road, Largo, FL 33771. If Anvil product is found to be defective, Anvil will provide the original purchaser with replacement sealer sufficient to repair the affected area. This remedy is the purchaser's exclusive remedy.

DESCRIPTION

Anvil #1950 Solvent Based Chattahoochee Stone Sealer & Glaze is formulated with an Oil Modified Urethane Resin for added toughness and abrasion resistance. It delivers a warm hue which helps restore the original look of Chattahoochee stone surfaces. Ideal for sealing and glaze coating both mortar and epoxy set Chattahoochee Stone. The sealer is resistant to pool chemicals, ultra violet light and most household detergents. Packaged to be used 'as is' with no thinning needed. Anvil's Chattahoochee Stone Sealer & Glaze Coat helps prolong the life of Chattahoochee stone decks and walkways.

SURFACE PREPARATION

Surface to be sealed must be clean and free of dirt, dust, grease and oil. High pressure water wash is recommended. A mixture of 1 part household bleach and 3 parts water is recommended for mold and mildew removal, rinse with water. Avoid the use of household detergents that could leave a hard to remove soap residue. Use Anvil #1450 Concrete & Masonry Cleaner & Etcher. Rinse area thoroughly and allow drying COMPLETELY before sealing. Allow surface to dry completely after washing or rain for at least 24 hours.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE. ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear an NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD** or log on to www.epa.gov/lead.

WARNING! This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

WARNING! IRRITANT! HARMFUL IF SWALLOWED, WHEN TINTED, CONTAINS ETHYLENE GLYCOL WHICH CAN CAUSE SEVERE KIDNEY DAMAGE WHEN INGESTED AND HAS BEEN SHOWN TO CAUSE BIRTH DEFECTS IN LABORATORY ANIMALS. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING. USE ONLY WITH ADEQUATE VENTILATION.

To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

FIRST AID: if you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN - DO NOT TAKE INTERNALLY. - KEEP FROM FREEZING

Application: Surface must be dry before application. Application to a damp surface could result in blushing (white haze) or even loss of adhesion. **(Do not coat if moist or wet)**. Use a short nap solvent resistant roller, apply in even overlapping strokes in the same direction. Avoid heavy application resulting in runs, ponding or puddling. Recoat within 8 hours of first coat application. If the 8 hour recoat interval has been exceeded, recoat after 24 hours.

CAUTION: Always pretest a small area to check for compatibility to existing surface or coating.

WARNING - FLAMMABLE

Avoid breathing of vapors. Use in well ventilated area. Keep away from heat and open flame. Avoid prolonged contact with skin. If swallowed, do not induce vomiting. Call a physician immediately. Keep container tightly closed when not in use

RECOMMENDED COVERAGE

Gallon: approx. 100 sq.ft.

FLASH POINT: 105 F

DRYING TIME: 70 F 50% R.H

Touch - 15 to 20 minutes

Recoat - 4 to 8 hours

Full Cure 24 hours

CLEANUP Mineral Spirits

EXTERIOR USE ONLY

VOC: 580 grams/liter

Revised 2/2018 (Supersedes all previous versions)

Manufactured with Pride by **Anvil Paints & Coatings, Inc.** • 1255 Starkey Road • Largo, FL 33771 • 1-800-822-6776 • www.anvilpaints.com

© All rights reserved. 2/2018