



## General Instructions for Grizzly Paint Stripper

1. Read and understand [safety data sheet](#) (SDS) before using this product.
2. For indoor application, open all windows and doors or use mechanical means to assure a constant supply of fresh moving air during use.
3. Protect floor coverings and other areas not being stripped. Do not use on synthetic fabrics, plastic, linoleum, asphalt, foam products or rubber tile.
4. Ideal working temperature is between 60-85 degrees F. Avoid direct sunlight.
5. Open pail carefully to avoid splashing. Stir well before using.
6. Apply with a brush. Brushes should be synthetic, nylon or polyester bristle.
7. For the best results test a small area to determine the appropriate thickness and duration of time required to remove the paint. Brush on a thick layer in one direction for best results. Brushing back and forth opens up the anti-evaporation barrier which forms on the initial pass. Apply any additional coats in the same direction.
8. Allow product to work for 5-15 minutes before performing a test scrape to determine how much of the old paint has been lifted.
9. Once Grizzly has lifted the old paint from the surface, scrape it away with a putty knife, cloth or steel wool.
10. Water may be used to help remove the residue. Collect waste in a metal container. Grizzly does not require neutralization.
11. Allow the surface to dry before additional applications of the remover or lockdown of lead dust.
12. Use warm, soapy water to clean tools and drippings. Allow waste solvents in metal container to evaporate outdoors, and then dispose of all waste according to current Local, State, and Federal Regulations.



TWIN CHEMICALS, INC.  
6175 Hickory Flat Highway, Suite 110-344, Canton, GA, 30115  
(800) 442-4958 / (770) 924-6147 Fax  
www.twinchemicals.com  
©2016 Twin Chemicals, Inc.

