

Technical Data Sheet

Solutions for LMC-6098 White Paste



Tel 336-2881613 sales@jorlink.com



Product Description

The LMC-6098 Premium White Marking Material is a new and improved version of the old LMC-6098 White Marking Material. It offers improved handling characteristics, will not dust off of the substrates it is applied to.

The LMC-6098 Premium product is a laser marking material for ceramic, glass and porcelain substrates. The LMC-6098 Premium is water based, which allows for moderate drying time and easy clean up. The products can be used on a variety of materials such as ceramic, tile, dinnerware, mugs, sanitary ware, glasses and porcelains including automotive glass, spandrel, container glass and the like.

Product Characteristics

Physical Properties

Appearance	Colored liquid, with water like consistency.
Density	11.0-15.0 pounds/gallon
Flash Point	Not applicable
Drying Rate	Moderate

Strengths of Product

Allows CO₂, YAG, and Fiber lasers to mark substrates such as ceramics, glass and porcelain with color. Produces marks resistant to abrasion and heat; fast drying; water based, organic free for environmentally preferred clean-up.

Recommended Application Parameters

Application Methods	Spray gun, airbrush, or aerosol.
Application	Clean the surface to be marked so that it is free of any lubricants or oils. The LMC series must be applied with an even coat to ensure a consistent mark and color.

Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.

Solutions for LMC-6098 White Paste

Coverage	500 grams of an LMC series product will cover approximately 2500 – 3000 square inches.
Wet Film Thickness	Approximately 3.0 wet mils.
Thinner	Thin with water as needed.
Recommended reduction	Use as supplied, thin if necessary.
Suggested Cleaning Solvents	Wash with water or a wet towel.

Curing/Drying of Product

Drying Method	Air dry, radiant heat, hair dryer or convection oven.
Drying Parameters	Typically air dries in about 5-10 minutes, can be sped up by force drying.

Laser Marking of Product

Laser Marking Method	CO ₂ , YAG, or Fiber laser
Recommended Starting Point for Settings	CO ₂ : 18-30% power (35 watt laser) 10-25% speed 500 DPI / 500 PPI YAG: 10-20 watts 10-20 inches/sec speed

Application Notes

For optimum mark quality, an even coat of the LMC product should be applied. If the material is applied too thin, the marks will not be as dark. If the material is applied too thick, more power will be required to make the mark and bonding may be incomplete. Applying the LMC series products will require practice to achieve the right coverage. It is also important to allow the coating to dry thoroughly. **We recommend that all CerMark LMC products be applied in a well ventilated area or spray booth designed to pull air away from user.**

Marking Notes

Marking may require some trial and error to optimize your laser with a particular substrate. Keep in mind that all lasers react differently depending on the substrate. Best results are obtained when marking at lower powers and slower speeds. High powers tend to damage glass substrates and should be avoided whenever possible. Experimentation should be performed to find settings that produce an acceptable mark without glass damage.



Solutions for LMC-6098 White Paste

Product Preparation

Insure that the product has been well mixed prior to use. Some settling may occur during extended storage periods. Material temperature should be equivalent to room temperature prior to viscosity measurement or application.

LASER MARKING PRODUCTS

Storage Recommendations

Product must be stored in cool and dry conditions. Storage temperature should be between 40°F (5°C) and 95°F (35°C). Settling may occur if stored for long periods of time. Before use, products must be stirred thoroughly. Partly used containers must be tightly sealed after use. If stored as recommended, a minimum shelf life of six months after the production date is guaranteed.

Contact Information

For questions about properties of this product, application techniques or laser settings, please contact:
800-245-4951 Customer Service & Technical Service

Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.