

# Technical Data Sheet



Tel 336-2881613 sales@jorlink.com



## Physical Testing of LMM-6000 Laser Marks with Aerospace Chemicals

Laser marks were made on type 304 stainless steel tags using LMM-6000 and a CO2 laser. Marks were made at settings of 100% power, 12% speed, 500 DPI on a 35 watt laser.

Tags were totally immersed in the test solutions.

### Exposure Time

Test solutions	24 Hours	1 Week	1 Month
• Skydrol 500 B-4 hydraulic fluid	No effect	No effect	No effect
• Royco 756 PAO	No effect	No effect	No effect
• Royco 782 PAO	No effect	No effect	No effect
• Aeroshell 500 turbine oil	No effect	No effect	No effect
• Royco 560 turbine oil	No effect	No effect	No effect
• Jet A jet fuel	No effect	No effect	No effect
• Aircraft De-icing fluid	No effect	No effect	No effect

### Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at [www.ferro.com](http://www.ferro.com). In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.



## Physical Testing of LMM-6000 Laser Marks with Aerospace Chemicals

### Notes:

The following fluids used meet these MIL specs:

Fluid	MIL specification
• Royco 756 PAO	MIL H-5606
• Royco 782 PAO	MIL PRF 83282
• Aeroshell 500 turbine oil	MIL PRF 23699 STD
• Royco 560 turbine oil	MIL PRF 23699 Class HTS

### Contact Information

For questions about properties of this product, application techniques or laser settings, please contact:  
800-245-4951 Customer Service & Technical Service

### Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at [www.ferro.com](http://www.ferro.com). In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.