



### DESCRIPTION:

- Water based adhesion promoting primer for use with Anvil Silicone Roof Coating 9900.
- Recommended for priming BUR, modified bitumen and aluminum coated roofs to improve adhesion of the top coating and to block asphalt bleed through.
- May be used on single-ply roof to increase long term adhesion in areas that retain water.
- May also be used as a vapor barrier coating on concrete roofs.

### ORDERING:

- Available in 5 gallon kits only.
- Coverage is approximately 200 square feet per gallon.

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
9950 ROOF-TEC 2K Epoxy Primer A+B	995004	Kit	760428995042	12.25 x 12.25 x 18.50	1 kit per case	24 cases

### STORAGE & HANDLING:

- Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead)**.
- If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure.
- Wear an NIOSH-approved respirator to control lead exposure.
- Clean up carefully with a HEPA vacuum and a wet mop.
- **Danger!** Flammable liquid and vapor. Harmful or fatal if swallowed. Aspiration hazard- can enter lungs and cause damage. Harmful if inhaled. May cause central nervous system effects, including dizziness, headache or nausea. Causes eye, skin and respiratory tract irritations. Overexposure may cause blood, liver, kidney damage. Use only with adequate ventilation.
- Keep out of reach of children.
- **KEEP FROM FREEZING**
- **FIRST AID:** In case of skin contact, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. For eye contact, flush immediately with large amounts of water, for at least 15 minutes. Obtain emergency medical treatment. If swallowed, obtain medical treatment immediately. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help.

### PRECAUTIONS:

- **NOTICE:** This product contains solvents. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- **For emergency information call (800) 545-2643.**
- For additional safety information, refer to the Safety Data Sheet for this product.
- Keep away from heat, sparks and flame. Do not smoke. Vapors may ignite. Extinguish all flames, burners, stoves, heaters and pilot lights and disconnect all electrical motors and appliances before use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation.
- If sanding is done, wear a dust mask to avoid breathing of sanding dust.
- Do not breathe vapors or spray mist.
- Ensure fresh air entry during application and drying.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- Close container after each use.



**WARNING:** This product can expose you to chemicals including Crystalline Silica and Titanium Dioxide, which is known to the State of California to cause cancer. For more information go to [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

# 9950 2-PART WATER BASED EPOXY PRIMER

PROPERTIES	
Weight per Gallon	11.6 lbs.
Color(s)	Gray
VOC Content	85 Grams per Liter (cal.)
Viscosity	15,000 cps
Solid Content by Weight	62%
Solid Content by Volume	44%
Flash Point	NA
Dry Time @ 70°F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 2 Hours Top Coat: 8 Hours

- DO NOT THIN.
- SHELF LIFE - Two years from the date of manufacture; date of manufacture is printed on the product container.

## Warning

### • Hazard statements

Harmful if swallowed

May Cause Cancer

### • Precautionary statements

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P280 Wear eye protection / face protection.

P264 Wash thoroughly after handling.

P305+P351+P338 If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do.

Continue rinsing.

P337+P313 If eye irritation persists: Get medical advice/attention.



## DIRECTIONS FOR USE AND SURFACE PREPARATION

- All surfaces must be clean and free of dirt, dust, rust, mildew and other surface contaminants.
- Remove contaminants by sandblasting, high-pressure water blasting or mechanical methods. Follow appropriate safety guidelines and wear proper protective equipment and clothing.
- Rinse with water and let dry completely.
- Substrate must be dry at time of applying primer and subsequent coating.

## APPLICATION

- Surface to be coated must be dry and free of dirt or corrosion particles. Apply only at temperatures above 40°F and rising with less than 90% humidity and no threat of rain for 12 hours.
- In a clean 5 gallon pail add two gallons of 9950 part A and two gallons of 9950 part B. Mechanically mix the two parts together taking care to avoid entraining air. Expected pot life under normal conditions is approximately four hours after mixing. Pot life is longer in cool temperatures and shorter in hot temperatures.
- Apply with a brush, roller or suitable spray equipment at the rate of 1/2 gallon per 100 sq. ft. After two hours, apply a second coat of 9950 at 1/2 gallon per 100 sq. ft. to achieve a pinhole free surface.
- When used on metal and single-ply membranes, one coat of 9950 at 1/3 to 1/2 gallon per 100 sq. ft. is sufficient. Application rates are approximate and will vary with the texture of the substrate.
- Allow a minimum of 8 hours before application of the top coat.
- The top coat must be applied within five days of the primer application.

## CLEANUP:

- Roller covers and spray equipment should be cleaned with soap and water.