



DESCRIPTION:

- Combines the durability of solvent-based urethane and epoxy coatings with the ease of water cleanup.
- It eliminates the need to be exposed to the toxicity and flammability of solvent borne resins and their solvent carriers.
- Highly resistant to the effects of hot car tires, delivers a solid color satin finish, and can be top coated with Anvil #2350 'Wet Look' Sealer to add a gloss finish to the surface.
- Formulated for use on painted or unpainted concrete and asphalt surfaces such as driveways, garage floors, patios, walkways, decks, pool decks and sidewalks, CMU, pre-cast, poured in place and tilt-up concrete buildings and concrete roofs.
- Not intended for use over wood surfaces.

ORDERING:

- Available in 1 gallon cans and 5 gallon buckets.
- Coverage is approx. 200 sq. ft. per gal. over coarse concrete and 400 sq. ft. per gal. over smooth concrete.

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
SEE PRODUCT DETAILS ON PAGE 3						

STORAGE & HANDLING:

- **Warning!** If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure. Wear an NIOSH-approved respirator to control lead exposure.
- To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying.
- If you experience eye watering, headaches or dizziness, increase fresh air.
- A dust mask does not provide protection against vapors.
- Use only with adequate ventilation.
- Wash thoroughly after handling.
- Clean up carefully with a HEPA vacuum and a wet mop.
- **KEEP AWAY FROM CHILDREN.**
- **KEEP FROM FREEZING**
- **FIRST AID: In case of skin contact**, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. **For eye contact**, flush immediately with large amounts of water, for at least 15 minutes. **If swallowed**, get medical attention immediately. **If inhalation causes physical discomfort**, move to fresh air. **If discomfort persists** or any breathing difficulty occurs, get medical help.

PRECAUTIONS:

- Before you start, find out how to protect yourself and your family by contacting the **National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.**
- **Warning! Irritant!** Harmful if swallowed, when tinted, contains ethylene glycol which can cause severe kidney damage when ingested and has been shown to cause birth defects in laboratory animals.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- May cause eye, nose and throat irritation.
- Do not take internally.
- Do not breathe vapors or spray mist.
- Avoid contact with skin and eyes. Wear eye protection and protective clothing.
- **For emergency information call (800) 545-2643.**
- For additional safety information, refer to the Safety Data Sheet for this product.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- Close container after each use.



WARNING: This product can expose you to chemicals including Titanium Dioxide and Magnesium Aluminum Silicate, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov

1500 CONCRETE STAIN ACRYLIC - SOLID COLOR

PROPERTIES	
Weight per Gallon	9.45 lbs
Color(s)	See chart below
Gloss	Low Sheen
VOC Content	48 Grams per Liter (cal.)
Viscosity	78 KU @ 75° F
Solid Content by Weight	34.1%
Solid Content by Volume	25.4%
Resin	100% Acrylic
Flash Point	None
Dry Time @ 70°F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 1/2 to 1 Hour To Recoat: 1 to 2 Hours Foot Traffic: 3 to 4 Hours Vehicle Traffic: 72 Hours Full Cure: 21 Days

- Extremely hard, glossy or alkaline concrete may require stronger acid solutions or repeated etching. In certain situations the use of muriatic acid may be harmful to surrounding items such as washers, dryers, water heaters, or other objects made of metal. Under these circumstances it may be necessary to apply Anvil #1960 Grip-Tite rather than acid etching to achieve maximum possible adhesion.
- Concrete should be at least 45 days old to reduce the possibility of the occurrence of efflorescence.
- Do not apply to concrete where hydrostatic pressure is present or over 3 lbs. of moisture per 1000 sq. ft. ASTM F1869-04.
- Check for a high pH, ASTM D4262 specification.
- Do not thin when using on tile roofs, block, or split-faced block.
- Pre-cast concrete should be acid etched and free of manufacturing oils.

APPLICATION:

- Do not dilute.
- Do not apply if the threat of rain is imminent or if the air/surface temperature is expected to be below 50°F within the first 24 hours of application.
- Do not apply in extreme heat of day or in direct sunlight.
- Hand stir product thoroughly before application.
- To ensure uniform color, all containers of the same color must be intermixed and stirred periodically during application.
- Apply in thin multiple coats by brush, roller or spray.
- Avoid heavy application resulting in runs, ponding, flood coating or puddling.
- Two or three thin coats are recommended depending on the surface being coated to achieve color uniformity.
- Some surfaces such as inclined driveways, garages, patios, steps etc. may require a slip resistant additive for safety. Add Anvil #9102 Talon Grip Slip Resistant Additive to the final coat of stain. This product should not be used in place of a non-skid finish.
- We recommend that a parked car stand on cardboard until full cure.

COLORS:

Dover Grey 1501	Brick Red 1502	Deck Grey 1503	Desert Beige 1506	Terra Cotta 1508	Black 1509
Pacific Fog 1514	Bermuda Tan 1516	Catalina Stone 1518	White Tint Base 1520	Intermediate Tint Base 1521	Accent Tint Base 1522

DIRECTIONS FOR USE AND SURFACE PREPARATION:

- Use proper preparation consistent with ASTM D4258-83 standard practice for surface cleaning.
- Proper preparation will ensure maximum adhesion, durability, and uniform coloration.
- Clean surface free of all wax, grease, oil, dirt, acid, mildew, release agents and all other surface contaminants.
- Failure to remove grease, oil, soap or other contamination will interfere with adhesion of the concrete stain.
- To clean surface, scrub with a solution of 1/2 cup of TSP (Trisodium Phosphate) per gallon of clean hot water. Rinse thoroughly with a power washer. Glossy painted surfaces must be dulled. Unpainted concrete surfaces should be mechanically abraded or acid etched before staining, in accordance with the ASTM D4260 Specification. Use Anvil #1450 Concrete & Masonry Cleaner & Etcher.
- Rinse area thoroughly and allow to dry COMPLETELY before staining.
- A properly etched surface will have the feel of 120 grit sandpaper.

CLEANUP:

Clean immediately with warm, soapy water.